






A27

SUSTAINED-RELEASE COMPOSITION COMPRISING LACTIC ACID-GLYCOLIC ACID COPOLYMER AND PROCESS FOR PRODUCING THE SAME

Patent number: EP1399133
Publication date: 2004-03-24
Inventor: YAMAMOTO K [JP]; YAMADA A [JP]; HATA YOSHIO [JP]
Applicant: TAKEDA CHEMICAL INDUSTRIES LTD [JP]
Classification:
- international: A61K9/16; A61K38/09; A61P5/06; A61P15/00; A61K9/50
- european: A61K9/16H6D4; A61K38/09
Application number: EP20020738837 20020628
Priority number(s): WO2002JP06526 20020628; JP20010199462 20010629; JP20010340980 20011106

Also published as:

 WO03002091 (A3)
 WO03002091 (A2)
 EP1399133 (A3)
 US2004241229 (A)
 CA2451718 (A1)

Abstract not available for EP1399133

Abstract of corresponding document: **US2004241229**

Present invention is to provide a sustained-release composition which contains a physiologically active substance in high content even when gelatin is not included, and suppresses its initial excessive release and, thus, can achieve a stable release rate over about one month. A sustained-release composition containing a lactic acid-glycolic acid polymer having a ratio or weight average molecular weight and number average molecular weight of about 1.90 or lower, or a salt thereof, and a physiologically active substance.

Data supplied from the **esp@cenet** database - Worldwide

BEST AVAILABLE COPY

DESCRIPTION

SUSTAINED-RELEASE COMPOSITION AND PROCESS FOR PRODUCING THE SAME

5 Technical Field

The present invention relates to a sustained-release preparation of a physiologically active substance and a process for producing the same.

10 Background Art

In JP-A 60-100516, a sustained-release microcapsule of a water-soluble drug, which comprises a particle of an average diameter of 2 to 200 μ m containing a water-soluble drug dispersed in a matrix comprising a lactic acid-
15 glycolic acid copolymer having weight average molecular weight of about 5000 to 200000 and comprising about 100 to 50% by weight of lactic acid and about 0 to 50% by weight of glycolic acid, and which is prepared by a method of drying in water is disclosed.

20 In JP-A 62-201816, a sustained-release microcapsule characterized in that the viscosity of a W/O type emulsion upon preparation of a W/O/W type emulsion is adjusted to about 150 to 10000 cp, and a process for preparing the same are disclosed.

25 In JP-A 62-54760, there are disclosed a biodegradable

polyoxycarboxylic ester which is a copolymer or a polymer having the content of water-soluble oxycarboxylic acid of less than 0.01 mole/100g in terms of a monobasic acid and having a weight average molecular weight of about 2000 to 50000, and an injection sustained-release microcapsule containing the polymer.

In JP-A 61-28521, there are disclosed a lactic acid-glycolic acid copolymer which has weight average molecular weight of about 5000 to 30000, does not contain a catalyst, has the dispersibility (by a gel permeation chromatography method) of about 1.5 to 2 and comprises about 50 to 95% by weight of lactic acid and 50 to 5% by weight of glycolic acid, and a pharmaceutical containing the polymer as a base.

In JP-A 6-192068, there is disclosed a process for preparing a sustained-release microcapsule, which comprises heating a microcapsule at a temperature higher than the glass transition temperature of a polymer, at which respective particles of the microcapsule do not adhere to each other.

In JP-A 4-218528, there is disclosed a method for purifying biodegradable aliphatic polyester, which comprises dissolving a biodegradable aliphatic polyester containing a low-molecular weight polymer having a molecular weight of 1,000 or smaller in an organic solvent, adding water thereto to precipitate a polymeric substance,

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
9 January 2003 (09.01.2003)

PCT

(10) International Publication Number
WO 03/002091 A2

(51) International Patent Classification⁷: **A61K 9/00**

(21) International Application Number: **PCT/JP02/06526**

(22) International Filing Date: **28 June 2002 (28.06.2002)**

(25) Filing Language: **English**

(26) Publication Language: **English**

(30) Priority Data:
2001-199462 29 June 2001 (29.06.2001) JP
2001-340980 6 November 2001 (06.11.2001) JP

(71) Applicant (*for all designated States except US*): **TAKEDA CHEMICAL INDUSTRIES, LTD.** [JP/JP]; 1-1, Doshomachi 4-chome, Chuo-ku, Osaka-shi, Osaka 541-0045 (JP).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **YAMAMOTO, Kazumichi** [JP/JP]; 341-11-1109, Shimizu-cho, Kawaramachi-dori Nijo-agaru, Nakagyo-ku, Kyoto-shi, Kyoto 604-0911 (JP). **YAMADA, Akiko** [JP/JP]; 313-501, Sashimono-cho, Kawaramachi-dori Ebisugawa-agaru, Nakagyo-ku, Kyoto-shi, Kyoto 604-0903 (JP). **HATA, Yoshio** [JP/JP]; 531-161, Azahonbetsu, Shikabe-cho, Kayabe-gun, Hokkaido 041-1404 (JP).

(74) Agents: **AOYAMA, Tamotsu et al.**; AOYAMA & PARTNERS, IMP Building, 3-7, Shiromi 1-chome, Chuo-ku, Osaka-shi, Osaka 540-0001 (JP).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— *without international search report and to be republished upon receipt of that report*

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: **SUSTAINED-RELEASE COMPOSITION AND PROCESS FOR PRODUCING THE SAME**

(57) Abstract: Present invention is to provide a sustained-release composition which contains a physiologically active substance in high content even when gelatin is not included, and suppresses its initial excessive release and, thus, can achieve a stable release rate over about one month. A sustained-release composition containing a lactic acid-glycolic acid polymer having a ratio or weight average molecular weight and number average molecular weight of about 1.90 or lower, or a salt thereof, and a physiologically active substance.



WO 03/002091 A2

and removing low-molecular weight polymer having molecular weight of 1,000, and there is described that water is added at 50 to 150 (ratio by volume) relative to 100 of the organic solvent.

5

Objects of the Invention

The present invention is to provide a sustained-release preparation which does not contain gelatin and contains a physiologically active substance in a large amount, and which can achieve a stable release rate over about one month by suppressing any initial excessive release of physiologically active substance.

10

Summary of the Invention

15

In order to solve the aforementioned problem, the present inventors studied intensively and, as a result, found a sustained-release preparation which contains a physiologically active substance in a large amount without containing gelatin and which can suppress any initial excessive release of physiologically active substance to achieve a stable release rate over about one month, by preparing a polymer having a ratio of weight average molecular weight to number average molecular weight of PLGA as a base about 1.90 or lower, or by using a lactic acid-glycolic acid polymer having weight average molecular

20

25

weight of about 11,600 to about 140,000 or a salt thereof,
which resulted in completion of the present invention.

That is, the present invention provides:

- 5 (1) A sustained-release composition containing a lactic acid-glycolic acid polymer having a ratio of weight average molecular weight to number average molecular weight of about 1.90 or lower, or a salt thereof, and a physiologically active substance,
- 10 (2) the sustained-release composition described in the (1), wherein the physiologically active substance is a physiologically active peptide,
- (3) the sustained-release composition described in the (2), wherein the physiologically active substance is an LH-RH derivative,
- 15 (4) the sustained-release composition described in the (1), wherein weight average molecular weight of a lactic acid-glycolic acid polymer is about 3,000 to about 100,000,
- (5) the sustained-release composition described in the (4), wherein weight average molecular weight of a lactic acid-glycolic acid polymer is about 8,000 to about 15,000,
- 20 (6) the sustained-release composition described in the (1), wherein the ratio of the low molecular weight fraction of molecular weight of lactic acid-glycolic acid polymer of about 3,000 or smaller is about 9% or lower,
- 25 (7) the sustained-release composition described in the (6),

wherein the ratio of the low molecular weight fraction of molecular weight of lactic acid-glycolic acid polymer of about 3,000 or smaller is about 3% to about 9%,

(8) the sustained-release composition described in the (1),
5 wherein said polymer has a molar ratio of lactic acid to glycolic acid of from 100:0 to 40:60,

(9) the sustained-release composition described in the (1), wherein said polymer has a molar ratio of lactic acid to glycolic acid of from 70:30 to 80:20,

10 (10) the sustained-release composition described in the (3), wherein the LH-RH derivative is a peptide represented by the formula:



wherein Y denotes DLeu, DAla, DTrp, DSer(tBu), D2Nal or
15 DHis(ImBzl), and Z denotes $\text{HN-C}_2\text{H}_5$, or Gly-NH_2 , or a salt thereof,

(11) the sustained-release composition described in the (3), wherein the LH-RH derivative is a peptide represented by the formula:

20 5-oxo-Pro-His-Trp-Ser-Tyr-DLeu-Leu-Arg-Pro-NH-C₂H₅,
or acetate thereof,

(12) the sustained-release composition described in the (3), wherein the LH-RH derivative or a salt thereof is contained at about 5%(w/w) to about 24%(w/w) in the sustained-release
25 composition,

(13) the sustained-release composition described in the (1),
wherein the physiologically active substance or a salt
thereof is slightly water-soluble or water-soluble,

(14) the sustained-release composition described in the (1),
5 which is for injection,

(15) the sustained-release composition described in the (1),
which releases a physiologically active substance or a salt
thereof over at least two weeks,

(16) the sustained-release composition described in the (1),
10 which does not contain a drug retaining substance,

(17) the sustained-release composition described in the (1),
which does not contain gelatin,

(18) a process for producing the sustained-release
composition as defined in the (1), which comprises removing
15 a solvent from a mixed solution containing a
physiologically active substance or a salt thereof and a
lactic acid-glycolic acid polymer having a ratio of weight
average molecular weight to number average molecular weight
of about 1.90 or lower, or a salt thereof,

(19) the process described in the (18), which comprises
20 mixing and dispersing a physiologically active substance or
a salt thereof in a solution, in an organic solvent,
containing a lactic acid-glycolic acid polymer having a
ratio of weight average molecular weight to number average
25 molecular weight of about 1.90 or lower, or a salt thereof,

and removing the organic solvent,

(20) the process described in the (19), wherein the physiologically active substance or a salt thereof is used as an aqueous solution containing the physiologically

5 active substance or a salt thereof,

(21) a pharmaceutical comprising the sustained-release composition as defined in the (1),

(22) an agent for preventing or treating prostate cancer, prostatomegaly, endometriosis, hysteromyoma, metrofibroma, precocious puberty, dysmenorrhea and breast cancer, or a
10 contraceptive, which comprises the sustained-release composition as defined in the (3),

(23) an agent for preventing recurrence of breast cancer after the operation for premenopausal breast cancer, which
15 comprises the sustained-release composition as defined in the (3),

(24) a method for preventing or treating prostate cancer, prostatomegaly, endometriosis, hysteromyoma, metrofibroma, precocious puberty and dysmenorrhea, or a contraceptive,
20 which comprises administering to a mammal an effective dose of the sustained-release composition as defined in the (3),


(25) a method for preventing recurrence of breast cancer after the operation for premenopausal breast cancer, which comprises administering to a mammal an effective dose of
25 the sustained-release composition as defined in the (3),

- (26) a process for producing a lactic acid-glycolic acid polymer having a weight average molecular weight of about 8,000 to about 15,000 and having a ratio of weight average molecular weight to number average molecular weight of about 1.90 or lower, or a salt thereof, which comprises adding water to an organic solvent containing a lactic acid-glycolic acid polymer having weight average molecular weight of about 5,000 to about 15,000 at a ratio of less than about 5 to 50 (ratio by volume) relative to 100 of the organic solvent,
- (27) the process for producing a polymer described in the (26), wherein the organic solvent is hydrophilic,
- (28) the process for producing a polymer described in the (27), wherein the hydrophilic organic solvent is acetone,
- (29) the process for producing a polymer described in the (26), wherein the ratio of water relative to 100 of the organic solvent is about 10 to about 45 (ratio by volume),
- (30) the process for producing a polymer described in the (26), wherein the ratio of water relative to 100 of the organic solvent is about 40 (ratio by volume),
- (31) a lactic acid-glycolic acid polymer having weight average molecular weight of about 8,000 to about 15,000 and having a ratio of weight average molecular weight to number average molecular weight of about 1.90 or lower, or a salt thereof,

(32) use of lactic acid-glycolic acid polymer or salt thereof described in the (31) for producing the sustained-release composition which does not include gelatin,


(33) a microsphere containing a lactic acid-glycolic acid polymer having weight average molecular weight of about 11,600 to about 14,000 or a salt thereof, and a LH-RH derivative or a salt thereof, and not containing gelatin,

(34) the microsphere described in the (33), wherein the LH-RH derivative or a salt thereof is a peptide represented by the formula:



wherein Y denotes DLeu, DAla, DTrp, DSer(tBu), D2Nal or DHis(ImBzl), and Z denotes HH, C₂H₅ or Gly-NH₂, or a salt thereof,

(35) the microsphere described in the (33), wherein the LH-RH derivative or a salt thereof is a peptide represented by the formula:



or acetate thereof,

(36) the microsphere described in the (33), wherein the LH-RH derivative or a salt thereof is contained at about 5%(w/w) to about 24%(w/w),

(37) the microsphere described in the (33), which is a microcapsule,

(38) the microsphere described in the (33), wherein the LH-

RH derivative or a salt thereof is released during at least more than 2 weeks,

(39) an agent for preventing or treating prostate cancer, prostatomegaly, endometriosis, hystero myoma, metrofibroma, precocious puberty and dysmenorrhea, or a contraceptive, which comprises the microsphere described in the (33),

(40) an agent for preventing recurrence of breast cancer after the operation for premenopausal breast cancer, which comprises the microsphere described in the (33),

(41) a method for preventing or treating prostate cancer, prostatomegaly, endometriosis, hystero myoma, metrofibroma, precocious puberty and dysmenorrhea, or a contraceptive, which comprises administering to a mammal an effective dose of the microsphere described in the (33),

(42) a method for preventing recurrence of breast cancer after the operation for premenopausal breast cancer, which comprises administering to a mammal an effective dose of the microsphere described in the (33).

Detailed Description of the Invention

The physiologically active substance used in the present invention is not particularly limited as long as it is pharmaceutically useful, and a non-peptide compound or peptide compound. Examples of a suitable non-peptide compound include an agonist, an antagonist, and a compound

having the enzyme inhibiting activity. In addition, as the peptide compound, for example, a physiologically active peptide is preferable. Physiologically active peptides having a molecular weight of about 3000 to about 40,000, preferably about 4000 to about 30,000, more preferably about 5000 to about 200,000 are suitable.

Examples of the physiologically active peptide include luteinizing hormone-releasing hormone (LH-RH), insulin, somatostatin, somatotropin, growth hormone-releasing hormone (GH-RH), prolactin, erythropoietin, adrenal cortical hormone, melanocyte-stimulating hormone, thyroid hormone-releasing hormone, thyroid-stimulating hormone, luteinizing hormone, follicle-stimulating hormone, vasopressin, oxytocin, calcitonin, gastrin, secretin, pancreozymin, cholecystokinin, angiotensin, human placental lactogen, human chorionic gonadotropin, enkephalin, endorphin, kyotrophin, tuftsin, thymopoietin, thymosin, thymotimurin, thymus humoral factor, blood thymus factor, tumor necrosis factor, colony-inducing factor, motilin, dynorphin, bombesin, neurotensin, cerulein, bradykinin, atrial natriuretic excretion-increasing factor, nerve growth factor, cell growth stimulator, neurotrophic factor, peptides having the endothelin antagonistic activity and derivatives, fragments thereof and derivatives of the fragments.

The physiologically active substance used in the present invention may be itself or maybe a pharmacologically salt thereof.

When the physiologically active substance has a basic group such as an amino group, examples of such salts include salts with inorganic acids (also referred to as inorganic free acid) (for example, carbonic acid, bicarbonic acid, hydrochloric acid, sulfuric acid, nitric acid, boric acid and the like), and organic acids (also referred to as organic free acid) (for example, succinic acid, acetic acid, propionic acid, trifluoroacetic acid and the like), when the physiologically active substance has an acidic group such as a carboxyl group and the like, examples of such the salt include salts with inorganic base (also referred to as inorganic free base) (for example, alkali metal such as sodium, potassium and the like, alkaline earth metal such as calcium, magnesium and the like), and organic bases (also referred to as organic free base) (for example, organic amines such as triethylamine and the like, basic amino acids such as arginine and the like). In addition, the physiologically active peptide may form a metal complex compound (for example, copper complex, zinc complex and the like).

Preferable examples of the physiologically active peptide include LH-RH derivatives or salts thereof which

are effective for hormone dependent diseases, in particular, sex hormone dependent cancers (for example, prostate cancer, uterine cancer, breast cancer, pituitary gland tumor and the like), sex hormone dependent disease such as

5 prostatomegaly, endometriosis, hystero myoma, precocious puberty, dysmenorrhea, amenorrhea, premenstrual syndrome, multilocular ovary syndrome and the like, contraception (or, when the rebound activity after cease of administration is utilized, infertility), prevention of recurrence of breast

10 cancer after the operation for premenopausal breast cancer. Further, examples include LH-RH derivatives or salts thereof effective for benign or malignant tumors which are sex hormone independent but LH-RH sensitive.

Specific examples of the LH-RH derivatives or salts

15 thereof include peptides described in Treatment with GnRH analogs: Controversies and perspectives (The parthenon Publishing Group Ltd.) published in 1996, JP-A 3-503165, JP-A 3-101695, JP-A 7-97334 and JP-A 8-259460.

Examples of the LH-RH derivatives include LH-RH

20 agonists and LH-RH antagonists. As the LH-RH antagonists, for example, a physiologically active peptide represented by the general formula [I]:

X-D2Nal-D4ClPhe-D3Pal-Ser-A-B-Leu-C-Pro-DAlaNH₂
[wherein X denotes N(4H₂-furoyl)Gly or NAc, A denotes a

25 residue selected from NH₂Tyr, Tyr, Aph(Atz), and

NMeAph(Atz), B denotes a residue selected from DLys(Nic), DCit, DLis(AzaglyNic), DLis(AzaglyFur) DhArg(Et₂), DAph(Atz) and DhCi, and C denotes Lys(Nisp), Arg or hArg(Et₂),

5 and a salt thereof are used.

As the LH-RH agonist, for example, a physiologically active peptide represented by the general formula [II]:

5-oxo-Pro-His-Trp-Ser-Tyr-Y-Leu-Arg-Pro-Z

[wherein Y denotes a residue selected from DLeu, DAla, DTrp, 10 DSer(tBu), D2Nal and DHis(ImBzl), and Z denotes NH-C₂H₅ or Gly-NH₂]

or a salt thereof is used. In particular, a peptide wherein Y is DLeu and Z is NH-C₂H₅ (that is, Peptide A represented by 5-oxo-Pro-His-Trp-Ser-Tyr-DLeu-Leu-Arg-Pro- 15 NH-C₂H₅; Leuprorelin) or a salt thereof (for example, acetate) is suitable.

These peptides can be prepared by the methods described in the aforementioned publications or patent publications or similar methods.

20 Abbreviations used in the present specification have the following meanings:

Abbreviation	Name
N(4H ₂ -furoyl)Gly:	N-tetrahydrofuroylglycine residue
NAC	N-acetyl group
N2Nal	D-3-(2-naphthyl)alanine residue
D4ClPhe	D-3-(4-chloro)phenylalanine residue
D3Pal	D-3-(3-pyridyl)alanine residue
NMeTyr	N-methyltyrosine residue
Aph(Atz)	N-[5'-(3'-amino-1'H-1',2',4'-triazolyl)]phenylalanine residue
NMeAph(Atz)	N-methyl-[5'-(3'-amino-1'H-1',2',4'-triazolyl)]phenylalanine residue
DLys(Nic)	D-(e-N-nicotinoyl)lysine residue
Dcit	D-citrulline residue
DLys(AzaglyNic)	D-(azaglycylnicotinoyl)lysine residue
DLys(AzaglyFur)	D-(azaglycylfuranyl)lysine residue
DhArg(Et ₂)	D-(N,N'-diethyl)homoarginine residue
DAph(Atz)	D-N-[5'-(3'-amino-1'H-1',2',4'-triazolyl)]phenylalanine residue
DhCi	D-homocitrulline residue
Lys(Nisp)	(e-N-isopropyl)lysine residue
hArg(Et ₂)	(N,N'-diethyl)homoarginine residue

Regarding other acids, abbreviation is expressed based on abbreviations according to IUPAC-IUB Commission on Biochemical Nomenclature (European Journal of Biochemistry, Vol.138, pp9-37 (1984)) or the conventional abbreviations in the art. In addition, when an amino acid can have an optical isomer, it denotes L-amino acid unless indicated otherwise.

As a lactic acid-glycolic acid polymer used in the present invention, a lactic acid-glycolic acid polymer

having a ratio of weight average molecular weight of the lactic acid-glycolic acid polymer to number average molecular weight of the lactic acid-glycolic acid polymer of about 1.90 or lower is preferably used.

5 A lactic acid-glycolic acid copolymer may be a salt. Examples of the salt include salts with inorganic bases (for example, alkali metal such as sodium, potassium and the like, and alkaline earth metal such as calcium, magnesium and the like) or organic bases (for example,
10 organic amines such as triethylamine and the like, and basic amino acids such as arginine and the like), salts with transition metals (for example, zinc, iron, copper and the like), and complex salts.

 A constitutional molar ratio of the lactic acid-
15 glycolic acid polymer is preferably about 100/0 to about 40/60, more preferably about 70/30 to about 80/20.

 A optical isomer ratio of lactic acid which is one of minimum repeating units of the "lactic acid-glycolic acid polymer" is preferably in a range of D-isomer/L-isomer
20 (mole/mole%) of about 75/25 to about 25/75. In particular, the D-isomer/L-isomer (mole/mole%) in a range of about 60/40 to about 30/70 is frequently used.

 A weight average molecular weight of the "lactic acid-glycolic acid polymer" is usually about 3,000 to
25 about 100,000, preferably about 3,000 to about 50,000,

particularly preferably about 8,000 to about 15,000.

A ratio of a low molecular weight fraction, having molecular weight of about 3,000 or smaller, of the "lactic acid-glycolic acid polymer" is preferably about 9% or
5 lower, more preferably about 3% to 9% or lower.

In addition, a lactic acid-glycolic acid polymer in the present invention has a ratio of weight average molecular weight of the lactic acid-glycolic acid polymer to number average molecular weight of the lactic acid-
10 glycolic acid polymer of about 1.90 or lower, preferably about 1.40 to about 1.90, more preferably about 1.45 to about 1.80.

Further, preferable examples include:

(1) a lactic acid-glycolic acid polymer having a weight
15 average molecular weight of about 3,000 to 100,000 and having a ratio of weight average molecular weight of a lactic acid- glycolic acid polymer to number average molecular weight of a lactic acid-glycolic acid polymer of about 1.90 or lower,

20 (2) a lactic acid-glycolic acid polymer having a weight average molecular weight of about 3,000 to 50,000 and having a ratio of weight average molecular weight of a lactic acid-glycolic acid polymer to number average molecular weight of a lactic acid-glycolic acid polymer of
25 about 1.90 or lower,

(3) a lactic acid-glycolic acid polymer having a weight average molecular weight of about 8,000 to 15,000 and having a ratio of weight average molecular weight of a lactic acid-glycolic acid polymer to number average

5 molecular weight of a lactic acid-glycolic acid polymer of about 1.90 or lower,

(4) a sustained-release composition described in the (1) to (3), wherein a ratio of a low molecular weight fraction, having molecular weight of about 3,000 or smaller, of a

10 lactic acid-glycolic acid polymer is about 9% or lower, and

(5) a sustained-release composition described in the (1) to (3), wherein a ratio of a low molecular weight fraction, having molecular weight of about 3,000 or smaller, of a lactic acid-glycolic acid polymer is about 3% to about 9%.

15 More preferable examples include:

(6) a lactic acid-glycolic acid polymer having weight average molecular weight of about 3,000 to 100,000 and having a ratio of weight average molecular weight of a lactic acid-glycolic acid polymer to number average

20 molecular weight of a lactic acid-glycolic acid polymer of about 1.40 to about 1.90,

(7) a lactic acid-glycolic acid polymer having a weight average molecular weight of about 3,000 to 50,000 and having a ratio of weight average molecular weight of a

25 lactic acid-glycolic acid polymer to number average

molecular weight of a lactic acid-glycolic acid polymer of about 1.40 to about 1.90,

(8) a lactic acid-glycolic acid polymer having weight average molecular weight of about 8,000 to 15,000 and
5 having a ratio of weight average molecular weight of a lactic acid-glycolic acid polymer to number average molecular weight of a lactic acid-glycolic acid polymer of about 1.40 to about 1.90,

(9) a sustained-release composition described in the (6) to
10 (8), wherein a ratio of a low molecular weight fraction, having molecular weight of about 3,000 or smaller, of a lactic acid-glycolic acid polymer is about 9% or lower, and
(10) a sustained-release composition described in the (6) to (8), wherein a ratio of a low molecular weight fraction,
15 having molecular weight of about 3,000 or smaller, of a lactic acid-glycolic acid polymer is about 3% to about 9%.

Most preferable examples include:

(11) a lactic acid-glycolic acid polymer having weight average molecular weight of about 3,000 to 100,000 and
20 having a ratio of weight average molecular weight of a lactic acid-glycolic acid polymer to number average molecular weight of a lactic acid-glycolic acid polymer of about 1.45 to about 1.80,

(12) a lactic acid-glycolic acid polymer having weight
25 average molecular weight of about 3,000 to 50,000 and

having a ratio of weight average molecular weight of a lactic acid-glycolic acid polymer to number average molecular weight of a lactic acid-glycolic acid polymer of about 1.45 to about 1.80,

- 5 (13) a lactic acid-glycolic acid polymer having weight average molecular weight of about 3,000 to 15,000 and having a ratio of weight average molecular weight of a lactic acid-glycolic acid polymer to number average molecular weight of a lactic acid-glycolic acid polymer of
10 about 1.45 to about 1.80,
- (14) a sustained-release composition described in the (11) to (13), wherein a ratio of a low molecular weight fraction, having molecular weight of about 3,000 or smaller, of a lactic acid-glycolic acid polymer is about 9% or lower, and
15 (15) a sustained-release composition described in the (11) to (13), wherein a ratio of a low molecular weight fraction, having molecular weight of about 3,000 or smaller, of a lactic acid-glycolic acid polymer is about 3% to about 9%.

Furthermore, a lactic acid-glycolic acid polymer
20 having weight average molecular weight of about 11,600 to about 14,000 or a salt thereof may be used.

Weight average molecular weight and number average molecular weight in the present specification refer to molecular weight in terms of polystyrene measured by gel
25 permeation chromatography (GPC) using as a standard

substance ten kinds of monodisperse polystyrene having (GPC1) weight average molecular weight of 397000, 189000, 98900, 37200, 17100, 9490, 5870, 2500, 1050 and 495.

Further, the amount of a low molecular weight fraction
5 of the polymer having a molecular weight of about 3,000 or smaller denotes the amount of a fraction having a molecular weight of about 3,000 or smaller within a weight average molecular weight distribution pattern obtained in the aforementioned GPC measurement. More specifically, the
10 amount of the area under the curve of a part corresponding to a molecular weight of about 3,000 or smaller relative to the area under the curve of the calculated weight average molecular weight distribution pattern is calculated. Measurement is performed by using a series of high speed
15 GPC apparatus (manufactured by Toso, HLC-8120GPC, a detection method is by differential refractive index), TSKguardcolum Super H-L(4.6mmi.d.x35mm), TSKgel SuperH4000(6mmi.d.x150mm)x2, and TSKgel SuperH2000(6mmi,d,x150mm) (All columns are manufactured by
20 Toso) and THF as a mobile phase at a flow rate of 0.6ml/min.

When the reaction between a lactic acid-glycolic acid polymer and a physiologically active substance is an ionic interaction, the main interaction is between the physiologically active substance and terminal carboxylic
25 acid of a lactic acid-glycolic acid polymer. When the low

molecular weight fraction is contained in a large amount, a physiologically active substance readily interacts with a lactic acid-glycolic acid polymer of a low molecular weight having high reactivity. In a sustained-release injection agent, a physiologically active substance involved in leakage upon preparation and initial release is mainly a physiologically active substance interacted with this lactic acid-glycolic acid polymer of a low molecular weight fraction. In order to increase the content of the physiologically active substance and suppress the amount of its initial release, it is necessary that a ratio of this lactic acid-glycolic acid polymer of a low molecular weight fraction is reduced below a certain level, and the ratio of weight average molecular weight to number average molecular weight is reduced below a certain level. For this reason, for example, in order to obtain a lactic acid-glycolic acid polymer for an one month-type sustained release preparation, a lactic acid-glycolic acid polymer is preferable, such a lactic acid-glycolic acid is preferable that the aforementioned weight average molecular weight is about 8,000 to about 15,000, a ratio of weight average molecular weight to number average molecular weight is about 1.90 or lower, preferably about 1.40 to about 1.90, more preferably about 1.45 to about 1.80, and the amount of a low molecular weight fraction having a weight average molecular weight of

3,000 or smaller is about 9% or lower, preferably about 3% to about 9%.

The "lactic acid-glycolic acid polymer" can be prepared by dehydration polycondensation without a catalyst from lactic acid and glycolic acid (JP-A 61-28521) or ring-opening polymerization from lactide and a cyclic diester compound such as glycolide and the like (Encyclopedic Handbook of Biomaterials and Bioengineering Part A: Materials, Volume 2, Marcel Dekker, Inc, 1995).

10 A lactic acid-glycolic acid polymer obtained by dehydration polycondensation without a catalyst from lactic acid and glycolic acid generally has a large amount of low molecular weight fraction, and has a ratio of weight average molecular weight to number average molecular weight of about 2 or higher. The weight average molecular weight of a lactic acid-glycolic acid copolymer used in the present specification is about 5,000 to about 15,000. The amount of the low molecular weight fraction having a molecular weight of about 3,000 or smaller can vary depending on weight average molecular weight and, when weight average molecular weight is about 10,000, the amount of low molecular weight fraction having molecular weight of about 3,000 or smaller is about 10% or higher.

25 The resulting lactic acid-glycolic acid polymer can be purified by using an organic solvent to obtain an end

polymer.

Examples of an organic solvent used in the present invention include preferably a hydrophilic or a readily water-soluble organic solvent such as, for example, acetone, 5 tetrahydrofuran, dioxane, dimethylformamide and dimethyl sulfoxide and, inter alia, acetone is preferably used.

The amount of water and organic solvent used in the present invention to be added is not particularly limited. However, when the amount of water is too large, reduction 10 of the low molecular weight fraction is insufficient and, thus, it is difficult to obtain an end polymer. On the other hand, when the amount of water is too small, the polymer becomes difficult to precipitate and, therefore, recovery is deteriorated and only a polymer having a higher 15 molecular weight than the desired molecular weight is recovered. Usually, the amount of water relative to 100 of an organic solvent is about 5 to 50, preferably about 10 to about 45, more preferably about 24 to about 40, particularly preferably about 40. For example, 10g of a 20 lactic acid-glycolic acid polymer is dissolved in 100mL of acetone which is an organic solvent, 40mL of purified water is gradually added thereto while stirring by a suitable method, to precipitate an end polymer, which can be dried by a suitable method. When an end polymer can not be 25 obtained by a single dissolution and precipitation step,

this procedure may be repeated.

In the sustained-release preparation of the present invention, a base is preferably a lactic acid-glycolic acid polymer having a ratio of weight average molecular weight to number average molecular weight of about 1.90 or lower, or a salt thereof, or a lactic acid-glycolic acid polymer having weight average molecular weight of about 11,600 to about 14,000 or a salt thereof. A constitutional molar ratio of lactic acid and glycolic acid is preferably 100/0 to 40/60. A physiologically active substance is preferably a LH-RH derivative and particularly preferably a LH-RH derivative is the peptide represented by the formula:

5-oxo-Pro-His-Trp-Ser-Tyr-DLeu-Leu-Arg-Pro-NH-C₂H₅ or acetate thereof. The content of a LH-RH derivative or a salt thereof is preferably about 5%(w/w) to about 24%(w/w). Further, preferable is such a sustained-release preparation that does not contain gelatin and releases a physiologically active substance or a salt thereof over at least two weeks.

20

A method of preparing a microcapsule

The thus obtained lactic acid-glycolic acid polymer can be used as a base for preparing a sustained-release preparation. A method of preparing a sustained-release composition, for example, a microcapsule containing a

25

physiologically active substance or a salt thereof, and a lactic acid-glycolic acid polymer or a salt thereof of the present invention is exemplified.

(I) A method of drying in water

5 (i) O/W method

In the present method, first, a solution of a lactic acid-glycolic acid polymer or a salt thereof in an organic solvent is prepared. It is preferable that an organic solvent used for preparing a sustained-release preparation
10 of the present invention has a boiling point of 120°C or lower.

As the organic solvent, for example, halogenated hydrocarbon (for example, dichloromethane, chloroform, dichloroethane, trichloroethane, carbon tetrachloride and
15 the like), ethers (for example, ethyl ether, isopropyl ether and the like), fatty acid ester (for example, ethyl acetate, butyl acetate and the like), aromatic hydrocarbon (for example, benzene, toluene, xylene and the like), alcohols (for example, ethanol, methanol and the like), and
20 acetonitrile are used, and a solvent of the mixture of them is used. As an organic solvent for a lactic acid-glycolic acid polymer or a salt thereof, inter alia, dichloromethane is preferable.

The concentration of lactic acid-glycolic acid polymer
25 in solution in an organic solvent can vary depending on the

molecular weight of a lactic acid-glycolic acid polymer and the type of organic solvent. For example, when dichloromethane is used as an organic solvent, the concentration is selected generally from about 0.5 to about 70% by weight, more preferably about 1 to about 60% by weight, particularly preferably about 2 to about 50% by weight.

A physiologically active substance or a salt thereof is added to, and dissolved or dispersed in the thus obtained solution of a lactic acid-glycolic acid polymer in an organic solvent. Then, the resulting solution in an organic solvent containing a composition comprising a physiologically active substance or a salt thereof and a lactic acid-glycolic acid polymer or a salt thereof is added to an aqueous phase to form an O (oily phase)/W (aqueous phase) emulsion, a solvent in an oily phase is volatilized or diffused in an aqueous phase to prepare a microcapsule. Upon this, a volume of an aqueous phase is selected generally from about 1 to about 10,000-fold, more preferably about 5 to 50,000-fold, particularly preferably about 10 to 2,000-fold an oily phase volume.

An emulsifier may be added to an aqueous phase besides the aforementioned components. Any emulsifier may be used as long as it can generally form a stable O/W emulsion. Specifically, for example, anionic surfactants (sodium

oleate, sodium stearate, sodium laurylsulfate and the like),
nonionic surfactants (polyoxyethylene sorbitan fatty acid
esters (Tween 80, Tween 60, manufactured by Atlas Powder),
polyoxyethylene castor oil derivative (HCO-60, HCO-50,
5 manufactured by Nikko Chemical), polyvinyl pyrrolidone,
polyvinyl alcohol, carboxymethylcellulose, lecithin,
gelatin and hyaluronic acid are used. These may be used
alone or in combination of some of them. The concentration
upon use is preferably in a range of about 0.0001 to 10% by
10 weight, more preferably in a range of about 0.001 to 5% by
weight.

An osmotic pressure regulating agent may be added to
an aqueous phase besides the aforementioned components.
Any osmotic pressure regulating agent may be used as long
15 as it produces osmotic pressure when formulated into an
aqueous solution.

Examples of the osmotic pressure regulating agent
include polyhydric alcohols, monohydric alcohols,
monosaccharides, disaccharides, oligosaccharide and amino
20 acids or derivatives thereof.

As the polyhydric alcohols, for example, trihydric
alcohols such as glycerin and the like, pentahydric
alcohols such as arabitol, xylitol, adonitol and the like,
and hexahydric alcohols such as mannitol, sorbitol,
25 dulcitol and the like are used. Inter alia, hexahydric

alcohols are preferable, in particular, mannitol is suitable.

Examples of the monohydric alcohols include methanol, ethanol and isopropyl alcohol and, inter alia, ethanol is
5 preferable.

As the monosaccharides, for example, pentoses such as arabinose, xylose, ribose, 2-deoxyribose and the like, and hexoses such as glucose, fructose, galactose, mannose, sorbose, rhamnose, fucose and the like are used and, among
10 them, hexoses are preferable.

As the oligosaccharides, for example, trisaccharides such as maltotriose, raffinose and the like, and tetrasaccharides such as stachyose and the like are used and, among them, trisaccharides are preferable.

As the derivatives of monosaccharides, disaccharides and oligosaccharide, for example, glucosamine, galactosamine, glucuronic acid and galacturonic acid are
15 used.

As the amino acids, any L-amino acids can be used and examples thereof include glycine, leucine and arginine.
20 Among them, L-arginine is preferable.

These osmotic regulating agents may be used alone or in combination.

These osmotic regulating agents are used at the
25 concentration such that osmotic pressure of an external

aqueous phase is about 1/50 to about 5-fold, preferably about 1/25 to about 3-fold osmotic pressure of a physiological saline solution. When mannitol is used as an osmotic pressure regulating agent, its concentration is preferably 0.5% to 1.5%.

As a method of removing organic solvent, the method known per se or a similar method is used. Examples of the method include a method of evaporating an organic solvent at a normal pressure or by reducing pressure to reduced pressure gradually while stirring with a propeller type stirrer, a magnetic stirrer or an ultrasound generating apparatus, a method of evaporating an organic solvent while the vacuum degree is regulated using a rotary evaporator, and a method of gradually removing an organic solvent using a dialysis membrane.

The thus obtained microcapsule is centrifuged or filtered to recover a free physiologically active substance or a salt thereof, a drug retaining substance and an emulsifier which are attached to the surface of a microcapsule, are washed with distilled water several times, and dispersed again in distilled water, which is lyophilized.

Since a microcapsule of the present invention uses as a base a lactic acid-glycolic acid polymer having a ratio of weight average molecular weight to number average

molecular weight of 1.90 or lower, or a salt thereof, or a lactic acid-glycolic acid polymer having weight average molecular weight of about 11,600 to about 14,000 or a salt thereof, the microcapsule can contain a drug in high
5 content and, thus, it is not necessary that the microcapsule contains a drug retaining substance such as gelatin and a thickening agent.

These polymers can be used preferably for manufacturing a sustained-release composition which
10 releases a drug over at least two weeks.

During the preparation step, an aggregation-preventing agent may be added in order to prevent aggregation of particles. As the aggregation-preventing agent, for example, a water soluble polysaccharide such as mannitol,
15 lactose, glucose and starches (for example, corn starch and the like), an amino acid such as glycine, and a protein such as fibrin and collagen are used. Among them, mannitol is suitable.

After lyophilization, if necessary, water and an
20 organic solvent in the microcapsule may be removed by warming within conditions under which microcapsules are not fused. Preferably, warming is performed at a temperature around or slightly higher than an intermediate glass transition temperature of a microcapsule obtained by a
25 differential scanning calorimeter under the conditions of a

temperature increasing rate of 10 to 20°C per min. More preferably, warming is performed at a temperature around the intermediate glass transition temperature of a microcapsule or in the temperature range from the

5 intermediate glass transition temperature of a microcapsule to a temperature higher by about 30°C than the intermediate glass transition temperature thereof. Preferably, warming is performed in the range of a temperature from around the intermediate glass transition temperature of a microcapsule
10 to higher by 10°C than the intermediate glass transition temperature thereof, more preferably in the range of a temperature from around the intermediate glass transition temperature to higher by 5°C than the intermediate glass transition temperature.

15 Warming time can vary depending on the amount of microcapsule and is generally about 12 hours to 168 hours, preferably about 24 hours to 120 hours, particularly preferably about 48 hours to 96 hours after the temperature of the microcapsule itself reaches a prescribed temperature.

20 The warming method is not particularly limited as long as the aggregation of microcapsules is uniformly warmed by the method.

As a method of warming and drying, for example, a method of warming and drying in a thermostatic chamber, a
25 fluidizing chamber, a moving chamber or a kiln, and a

method of warming and drying with a microwave are used.

Among them, a method of warming and drying in a thermostatic chamber is preferable.

5 (ii) W/O/W method

First, a solution of a lactic acid-glycolic acid polymer or a salt thereof in an organic solvent is prepared, and the thus obtained organic solvent solution is referred to as an oily phase. The method of preparation is the same
10 as that described in section (I)(i) above. The concentration of lactic acid-glycolic acid polymer in an organic solvent can vary depending on the molecular weight of lactic acid-glycolic acid polymer and type of organic solvent and, for example, when dichloromethane is used as
15 an organic solvent, the concentration is selected from generally about 0.5 to about 70% by weight, more preferably about 1 to about 60% by weight, particularly preferably about 2 to about 50% by weight.

Next, a solution or a dispersion of a physiologically
20 active substance or a salt thereof [the solvent is water or a mixture of water and alcohols (for example, methanol, ethanol and the like)] is prepared.

The concentration of physiologically active substance or a salt thereof to be added is generally 0.001mg/ml to
25 10g/ml, more preferably 0.1 mg/ml to 5g/ml, more preferably

10 mg/ml to 3g/ml.

When the above-described physiologically active substance has a basic group such as amino group, salts of physiologically active substance include a salt with
5 inorganic acid (also referred to as inorganic free acid) (for example, carbonic acid, acid carbonate, hydrochloric acid, sulfuric acid, nitric acid, boric acid etc.), organic acid (also referred to as organic free acid) (for example, succinic acid, acetic acid, propionic
10 acid, trifluoroacetic acid etc.).

When a physiologically active substance has a acidic group such as carboxyl group, salts of physiologically active substance include a salt with inorganic base (also referred to as inorganic free base) (for example, alkali
15 metals such as sodium, potassium, alkali earth metals such as calcium, magnesium, etc.), organic base (also referred to as organic free base) (for example, organic amines such as triethylamine, basic amino acids such as arginine, etc.). Further, physiologically active peptides may form a metal
20 complex compound (for example, copper complex, zinc complex etc.). When a physiologically active substance is a LHRH derivative, acetic acid is particularly preferably added.

As a solubilizing agent and a stabilizing agent, known ones may be used. In order to dissolve or disperse a
25 physiologically active substance or an additive, heating,

shaking and stirring may be performed to such an extent that the activity is not lost, and thus obtained aqueous solution is referred to as an inner aqueous phase.

The thus obtained inner aqueous phase and oily phase
5 are emulsified by known methods such as a homogenization and ultrasound to form a W/O emulsion.

The volume of oily phase to be mixed is about 1 to about 1000-fold, preferably 2 to 100-fold, more preferably about 3 to 10-fold relative to the volume of the inner
10 aqueous phase.

The range of the viscosity of the resulting W/O emulsion is generally about 10 to 10,000cp, preferably about 100 to 5,000cp, particularly preferably about 500 to 2,000cp at about 12 to 25°C.

15 Then the resulting W/O emulsion comprising a physiologically active substance or a salt thereof and a lactic acid-glycolic acid polymer or a salt thereof is added to an aqueous phase to form a W (inner aqueous phase)/O (oily phase)/W (external aqueous phase), a solvent
20 in an oily phase is volatilized or diffused into an external aqueous phase to prepare a microcapsule. Upon this, a volume of an external aqueous phase is selected from generally about 1-fold to about 10,000-fold, more preferably about 5-fold to about 50,000-fold, particularly
25 preferably about 10-fold to about 2,000-fold a volume of an

oily phase.

- An emulsifier and an osmotic pressure regulating agent which may be added to the aqueous phase besides the aforementioned components, and the methods of preparation thereafter are the same as those described in section (I) (i) above.

(II) Phase separating method

When a microcapsule is prepared by the present method, a coacervating agent is gradually added to an organic solvent solution containing a physiologically active substance or a salt thereof and a lactic acid-glycolic acid polymer or a salt thereof described in a method of drying in water in the (I) while stirring, to precipitate and solidify a microcapsule. The volume of the coacervating agent may be from about 0.01 to 1,000-fold, preferably about 0.05 to 500-fold, particularly preferably about 0.1 to 200-fold of the volume of the oily phase.

The coacervating agent is not particularly limited as long as it is a polymer series, mineral oil series or plant oil series compound which is compatible with an organic solvent, and does not dissolve the complex of the physiologically active substance or a salt thereof and the lactic acid-glycolic acid polymer or a salt thereof. Specifically, for example, silicone oil, sesame oil,

soybean oil, corn oil, cottonseed oil, coconut oil, linseed oil, mineral oil, n-hexane or n-heptane may be used. These may be used by mixing 2 or more of them.

The thus obtained microcapsule is recovered, washed
5 repeatedly with heptane or the like to remove the
coacervating agent from the composition comprising a
physiologically active substance or a salt thereof and a
lactic acid-glycolic acid polymer or a salt thereof, which
is then dried under reduced pressure. Alternatively,
10 washing is performed in the same manner as that described
as a method of drying in water in section (I) (i) above,
which is lyophilized and further warmed and dried.

(III) Spraying drying method

15 When a microcapsule is prepared by the present method,
an organic solvent solution containing a physiologically
active substance or a salt thereof and a lactic acid-
glycolic acid polymer or a salt thereof described in a
method of drying in water in section (I) is sprayed in a
20 drying chamber of a spray dryer using a nozzle, and an
organic solvent in finely-divided droplets is volatilized
in an extremely short time to prepare a microcapsule.
Examples of the nozzle include to fluid nozzle type,
pressure nozzle type, rotation disc type. Thereafter, if
25 necessary, the microcapsule may be washed, lyophilized and

further warmed and dried by the same method as that described in a method of drying in water in section (I).

As a dosage form other than the aforementioned microcapsule, an organic solvent solution containing a physiologically active substance or a salt thereof and a lactic acid-glycolic acid polymer or a salt thereof described in a method of drying in water in a method of preparing a microcapsule (I) is dried by evaporating an organic solvent and water while the degree of vacuum is regulated using, for example, a rotary evaporator, which may be ground with a jet mill to obtain a fine powder (also referred to as microparticle).

Further, the ground fine powder may be washed by the same method as that described in a method of drying in water in a method of preparing a microcapsule (I), lyophilized and further warmed and dried.

The thus obtained microcapsule or fine powder can achieve release of a drug corresponding to a decreasing rate of a lactic acid-glycolic acid polymer used.

The sustained-release composition of the present invention may be any form such as a microsphere, a microcapsule or a fine powder (microparticle), and a microcapsule is suitable.

The sustained-release composition of the present invention may be used as it is or the composition as a raw

material may be formulated into a variety of dosage forms, and may be administered as an injectable agent or an implantable agent for intravenous, subcutaneous and intra-organ administration, as a transmucosal agent, an oral agent (for example, capsule (for example, hard capsule, soft capsule and the like)), solid preparations such as a granule, a powder and the like, or liquid agent such as a syrup agent, an emulsion, a suspension and the like for nasal, rectal or uterine administration.

10. For example, for formulating the sustained-release composition of the present invention into an injectable agent, it is formulated into an aqueous suspension together with a dispersant (for example, surfactants such as Tween 80, HCO-60 and the like, and polysaccharides such as sodium
15 hyaluronate, carboxymethylcellulose, sodium arginate and the like), a preservative (for example, methylparaben and propylparaben), an isotonic (sodium chloride, mannitol, sorbitol, glucose and proline), or it is dispersed into an oily suspension together with a plant oil such as sesame
20 oil or corn oil to obtain a sustained-release injection agent which can be actually used.

The particle diameter of a sustained-release composition of the present invention may be, when used as a suspension injection agent, in such a range that satisfies
25 a dispersion degree and the needle penetrating property.

For example, an average particle diameter is a range of about 0.1 to 300 μ m, preferably about 0.5 to 150 μ m, more preferably about 1 to 100 μ m.

5 In order to formulate a sustained-release composition of the present invention into an aseptic preparation, methods include, but are not limited to a method of performing all steps aseptically in preparation, a method of sterilizing with gamma-ray, a method of adding an antiseptic and the like.

10 Since a sustained-release composition of the present invention of low toxicity, it can be used as a safe medicine for a mammal (for example, human being, cow, pig, dog, cat, mouse, rat, rabbit and the like), the dose of sustained-release composition of the present invention can
15 vary depending on the type and content of the physiologically active substance, the dosage form, duration time of release of physiologically active substance, target disease and subject animal and effective amount of a physiologically active substance. A single
20 dosage of physiologically active substance can be preferably selected appropriately from a range of about 0.01mg to 10mg/kg weight, more preferably about 0.05mg to 5mg/kg weight per adult, for example, when used in a sustained-release preparation for a six months preparation.

25 A single dose of a sustained-release composition can

be preferably selected appropriately from about 0.05mg to 50mg/kg weight, more preferably about 0.1mg to 30mg/kg weight per adult.

Administration time can be appropriately selected
5 depending on the type and content of a physiologically active substance as a basis, dosage form, duration time of release of a physiologically active substance, target disease and a subject animal, such as once every few weeks, once per month, once every few months (for example, three
10 months, four months, six months etc) and the like.

A sustained-release composition of the present invention can be used as an agent for preventing or treating a variety of diseases depending on the type of physiologically active substance contained therein and, for
15 example, when a physiologically active substance is an LH-RH derivative, it can be used for preventing or treating hormone dependent diseases, in particular, sex hormone dependent cancers (for example, prostate cancer, uterine cancer, breast cancer, pituitary gland tumor and the like),
20 sex hormone dependent diseases such as prostatomegaly, endometriosis, hysteromyoma, precocious puberty, dysmenorrhea, amenorrhea, premenstrual syndrome, multilocular ovary syndrome and the like, as an agent for preventing recurrence of breast cancer after the operation
25 for premenopausal breast cancer, as an agent for preventing

or treating Alzheimer's disease or autoimmune diseases, and
as a contraceptive (or, an agent for preventing or treating
infertility, when the rebound activity after cease of
administration is utilized). Further, it can also be used
5 as an agent for preventing or treating benign or malignant
tumors which are known to be sex hormone independent but
sensitive to LH-RH.

Therefore, hormone dependent diseases, in particular,
sex hormone dependent cancers (for example, prostate cancer,
10 uterine cancer, breast cancer, pituitary gland tumor and
the like), sex hormone dependent diseases such as
prostatomegaly, endometriosis, hysteromyoma, precocious
puberty, dysmenorrhea, amenorrhea, premenstrual syndrome,
multilocular ovary syndrome and the like can be prevented
15 or treated; and pregnancy can be prevented by administering
to a mammal an effective dose of the treating or preventing
agent according to this invention, and also recurrence of
breast cancer after the operation for premenopausal breast
cancer can be prevented thereby.

20
[Examples]

The present invention will be explained more
specifically by way of Examples, Comparative Examples and
Experimental Examples but the present invention is not
25 limited by them.

Example A1

10g of a lactic acid-glycolic acid copolymer, having a weight average molecular weight of 9700 and a number average molecular weight of 5030, synthesized by dehydration polycondensation of lactic acid and glycolic acid is dissolved in 100mL of acetone, and 40mL of purified water is added dropwise while stirring, to precipitate a polymer. The solution other than the precipitated glutinous starch syrup-like polymer is removed by decantation, and the resulting polymer is dried under vacuum. The polymer after drying has a yield of 8.37g, a weight average molecular weight of 10500, and a number average molecular weight of 6700.

15 Example A2

4.87g of the polymer obtained in Example A1 is dissolved in 8.03g of dichloromethane into an oily phase. The oily phase is mixed into an aqueous phase in which 0.597g of acetate of Peptide A is dissolved in 0.6mL of purified water, which is primarily-emulsified at 25000rpm using a Polytron to obtain a W/O emulsion. This W/O emulsion is added to 1000mL of an 0.1% aqueous polyvinyl alcohol solution at 15°C, which is converted into a W/O/W emulsion at 7000rpm using a homomixer. The microcapsule is solidified by desolvation with a propeller stirrer over

three hours, then microcapsules which have passed through a 200 mesh sieve are recovered, and lyophilized after 0.48g of mannitol has been added. After lyophilization, the yield of the resulting microcapsule is 3.92g and the
5 content of Peptide A is 10.18%.

Comparative Example A1

A microcapsule obtained using a lactic acid-glycolic acid copolymer of Example A1 according to the same manner
10 as that of Example A2 has a yield of 3.97g, and a content of Peptide A of 9.50%.

Experimental Example A1

Microcapsules obtained in Example A2 and Comparative
15 Example A1 were dispersed in 0.3ml of a dispersing medium (distilled water in which 0.25mg of carboxymethylcellulose, 0.5mg of Polysorbate 80 and 25mg of mannitol are dissolved) at an amount of 2.25mg in terms of Peptide A, which were administered to a male SD rat, 7 weeks old, in the back
20 subcutaneously with a 22G injection needle, respectively. A prescribed time after administration, rats were slaughtered, microcapsules remaining in the administration site was removed, and Peptide A remaining in it was quantitated, which was divided by each initial content to
25 obtain a remaining rate as shown in Table 1. Further,

Mw/Mn of polymers used in Example A2 and Comparative Example A1 are described in Table.

[Table 1]

	Comparative Example A1	Example A2
Mw/Mn	1.93	1.57
1day	84.64%	91.17%
2week	32.2%	54.31%
4week	2.54%	10.28%

It is apparent from Table 1, that when a polymer used
5 in Example A2 and having Mw/Mn of 1.90 or lower rendered by
acetone treatment is used to prepare a microcapsule, the
initial release amount of Peptide A from the microcapsule
is suppressed, and sustained release over a long term of
four weeks is ensured.

10

Example A3

185.7g of a lactic acid-glycolic acid copolymer having
a weight average molecular weight of 10600 and a number
average molecular weight of 6600 was dissolved in 300.1g of
15 dichloromethane, and the temperature was adjusted to 29.5°C.
330.2g was weighed from this organic solvent solution, then
mixed with an aqueous solution which had been obtained by
dissolving 15.62g of acetate of Peptide A in 15.31g of
distilled water which had been warmed to 54.3°C, and
20 stirred for 1 minute to obtain a crude emulsion, which was

next emulsified under the conditions of 10,000rpm for two minutes using a homogenizer to form a W/O emulsion. Then, this W/O emulsion was cooled to 17.8°C, poured into 25 liters of a 0.1% (w/w) aqueous polyvinyl alcohol (EG-40, 5 manufactured by Nihongoseikagaku) solution which had been adjusted to 17.9°C in advance, for 1 minute and 16 seconds, and stirred at 7,005rpm using HOMOMIC LINE FLOW (manufactured by Tokushukika) to obtain a W/O/W emulsion. This W/O/W emulsion was stirred for 3 hours to volatilize 10 dichloromethane or diffuse dichloromethane into an external aqueous phase, an oily phase was solidified, filtered through a sieve having 75µm opening, and a microcapsule was settled continuously at 2,000rpm using a centrifuge (H-600S, manufactured by Kokusanenshinki) and collected. The 15 collected microcapsule was dispersed again in a small amount of distilled water, filtered through a sieve having 90µm opening, which was dissolved by addition of 17.2g of mannitol and lyophilized to obtain a powder. The microcapsule had a recovery rate of 76.4% and a content of 20 Peptide A in the microcapsule of 8.79%.

Experimental Example A2

About 26mg of a microcapsule described in Example A3 was dispersed in 0.3ml of a dispersing medium (distilled 25 water in which 0.15mg of carboxymethylcellulose, 0.3mg of

Polysorbate 80 and 15mg of mannitol are dissolved), which was administered to a male SD rat, 7 weeks old, in the back subcutaneously with a 22G injection needle. A prescribed time after administration, the rat was slaughtered, microcapsule remaining in the administration site was removed, Peptide A in it was quantitated, which was divided by each initial content to obtain a remaining rate as shown in Table 2.

[Table 2]

Time	1day	1week	1week	1week	1week	1week
Remaining rate	90.29%	68.06%	36.63%	12.75%	4.48%	1.12%

As apparent from Table 2, even when preparation was scaled up, although the microcapsule described in Example A3 contains a physiologically active substance at a high content, the remaining rate of a physiologically active substance one day after administration is as remarkably high as 90%. Therefore, when an Mw/Mn ratio of a polymer is a low value as about 1.6, the effect of considerably suppressing initial excessive release of a physiologically active substance is exerted. In addition, this microcapsule achieves release of the physiologically active substance at a constant rate over a long period of time.

Example B1

197.7g of a lactic acid-glycolic acid copolymer having

a weight average molecular weight of 12600 and a number average molecular weight of 6400 was dissolved in 320.1g of dichloromethane, press-filtered using a 0.2 μ m filter (EMFLOW, DFA4201FRP), and the temperature was adjusted to about 30.0°C. 330.1g was weighed, mixed with an aqueous solution which had been obtained by dissolving 15.68g of acetate of Peptide A in 15.31g of distilled water and had been warmed to 56.0°C, stirred for 1 minute to obtain a crude emulsion, which was then emulsified under the condition of 10,000rpm for two minutes to obtain a W/O emulsion. Then, this W/O emulsion was cooled to 18.2°C, poured into 25 liters of a 0.1% (w/w) polyvinyl alcohol (EG-40, manufactured by Nihongoseikagaku) which had been adjusted to 18.4°C in advance, for 1 minute and 46 seconds, stirred at 7,007rpm using HOMOMIC LINE FLOW (manufactured by Tokushukika) to obtain a W/O/W emulsion. This W/O/W emulsion was stirred for 3 hours to volatilize dichloromethane or diffuse it into an external aqueous phase, then the oily phase was solidified, filtered using a seive having 75 μ m opening, and microcapsule was continuously settled at 2,000rpm using a centrifuge (H-600S, manufactured by Kokusanenshinki) and collected. The collected microcapsule was dispersed again in a small amount of distilled water, filtered using a seive having 90 μ m opening, then dissolved by addition of 17.2g of

mannitol and lyophilized to obtain a powder. The microcapsule had a recovery rate of 73.47% and a content of Peptide A in a microcapsule of 8.43%.

5 Experimental Example B1

About 26.7mg of the microcapsule described in Example B1 was dispersed in 0.3 mg of dispersing medium (distilled water in which 0.15mg of carboxymethylcellulose, 0.3mg of Polysorbate 80, and 15mg of mannitol were dissolved), and
10 administered to a male SD rat, 7 weeks old, in the back subcutaneously with a 22G injection needle. A prescribed time after administration, the rat was slaughtered, and microcapsule remaining at the administration site, and Peptide A in it was quantitated, which was divided by each
15 initial content to obtain a remaining rate as shown in Table 3.

[Table 3]

Time	1day	1week	1week	1week	1week	1week
Remaining rate	82.43%	68.33%	47.07%	23.58%	9.05%	2.08%

As apparent from Table 3, microcapsule described in Example B1 could contain a physiologically active substance at a
20 high content even when gelatin was not included, and remarkably suppressed initial release of a physiologically active substance and, this microcapsule released a physiologically active substance over a long period of time.

Experimental Example B2

About 44.6mg of a microcapsule described in Example B1 was dispersed in 1.0ml of a dispersing medium (distilled water in which 0.15mg of carboxymethylcellulose, 0.3mg of Polysorbate 80, and 15mg of mannitol were dissolved), which was administered to a beagle, weighing 7 to 12kg, in the back subcutaneously with a 23G injection needle. A prescribed time after administration, blood was taken from a forefoot vein, the concentrations of Peptide A and testosterone were quantitated, and the results are shown in Table 4.

[Table 4]

Time	1day	1week	2week	3week	4week	5week
Peptide A	2.21	0.398	0.525	0.433	0.603	0.358
Testosterone	2.79	0.57	0.35	0.35	0.30	0.39

As apparent from Table 4, a microcapsule described in Example B1 releases a physiologically active substance for a long period of time, and maintained the blood concentration of the physiologically active substance. In addition, the activity of the physiologically active substance released into blood was not lost and drug efficacy was retained.

Industrial Applicability

A sustained-release preparation of the present invention, having a ratio of weight average molecular weight to number average molecular weight of PLGA as a base of about 1.90 or lower, or using a lactic acid-glycolic acid polymer having weight average molecular weight of about 11,600 to about 14,000 or a salt thereof as a base, contains a physiologically active substance in high content even when gelatin is not included, and suppresses initial excessive release of physiologically active substance and, thus, can achieve a stable release rate over about one month.

That is, the preparation according to this invention has such useful effects that the manufacturing process and cost can be reduced because there is no need for using a drug retaining substance such as gelatin and a thickening agent, resulting reduced additives, and that the preparation can contain a drug at a high concentration without using a drug retaining substance and a thickening agent; a sustained-release composition which releases a drug over at least two weeks can be produced; and the preparation having high stability can be produced owing to the increase of glass transition temperature.

CLAIMS

1. A sustained-release composition containing a lactic acid-glycolic acid polymer having a ratio of weight average molecular weight to number average molecular weight of about 1.90 or lower, or a salt thereof, and a
5 physiologically active substance.

2. The sustained-release composition according to claim 1, wherein the physiologically active substance is a physiologically active peptide.

10 3. The sustained-release composition according to claim 2, wherein the physiologically active substance is an LH-RH derivative.

4. The sustained-release composition according to claim 1, wherein weight average molecular weight of said
15 lactic acid-glycolic acid polymer is about 3,000 to about 100,000.

5. The sustained-release composition according to claim 4, wherein weight average molecular weight of lactic acid-glycolic acid polymer is about 8,000 to about 15,000.

20 6. The sustained-release composition according to claim 1, wherein the ratio of the low molecular weight fraction of molecular weight of lactic acid-glycolic acid polymer of about 3,000 or smaller is about 9% or lower.

25 7. The sustained-release composition according to claim 6, wherein the ratio of the low molecular weight

fraction of molecular weight of lactic acid-glycolic acid polymer of about 3,000 or smaller is about 3% to about 9%.

8. The sustained-release composition according to claim 1, wherein said polymer has a molar ratio of lactic acid to glycolic acid of from 100:0 to 40:60.

9. The sustained-release composition according to claim 1, wherein said polymer has a molar ratio of lactic acid to glycolic acid of from 70:30 to 80:20.

10. The sustained-release composition according to claim 3, wherein the LH-RH derivative is a peptide represented by the formula:

5-oxo-Pro-His-Trp-Ser-Tyr-Y-Leu-Arg-Pro-Z

wherein Y denotes DLeu, DAla, DTrp, DSer(tBu), D2Nal or DHis(ImBzl), and Z denotes HH, C₂H₅, or Gly-NH₂, or a salt thereof.

11. The sustained -release composition according to claim 3, wherein the LH-RH derivative is a peptide represented by the formula:-

5-oxo-Pro-His-Trp-Ser-Tyr-DLeu-Leu-Arg-Pro-NH-C₂H₅,

or acetate thereof.

12. The sustained-release composition according to claim 3, wherein the LH-RH derivative or a salt thereof is contained at about 5%(w/w) to about 24%(w/w) in the sustained-release composition.

13. The sustained-release composition according to

claim 1, wherein the physiologically active substance or a salt thereof is slightly water-soluble or water-soluble.

14. The sustained-release composition according to claim 1, which is for injection.

5 15. The sustained-release composition according to claim 1, which releases a physiologically active substance or a salt thereof over at least two weeks.

16. The sustained-release composition according to claim 1, which does not contain a drug retaining substance.

10 17. The sustained-release composition according to claim 1, which does not contain gelatin.

18. A process for producing the sustained-release composition according to claim 1, which comprises removing a solvent from a mixed solution containing a
15 physiologically active substance or a salt thereof and a lactic acid-glycolic acid polymer having a ratio of weight average molecular weight to number average molecular weight of about 1.90 or lower, or a salt thereof.

19. The process according to claim 18, which
20 comprises mixing and dispersing a physiologically active substance or a salt thereof in an organic solvent solution containing a lactic acid-glycolic acid polymer having a ratio of weight average molecular weight to number average molecular weight of about 1.90 or lower or a salt thereof,
25 and removing the organic solvent.

20. The process according to claim 19, wherein the physiologically active substance or a salt thereof is used as an aqueous solution containing the physiologically active substance or a salt thereof.

5 21. A pharmaceutical comprising the sustained-release composition according to claim 1.

22. An agent for preventing or treating prostate cancer, prostatomegaly, endometriosis, hysteromyoma, metrofibroma, precocious puberty, and dysmenorrhea, or a
10 contraceptive, which comprises the sustained-release composition according to claim 3.

23. An agent for preventing recurrence of breast cancer after the operation for premenopausal breast cancer, which comprises the sustained-release composition according
15 to claim 3.

24. A method for preventing or treating prostate cancer, prostatomegaly, endometriosis, hysteromyoma, metrofibroma, precocious puberty and dysmenorrhea, or a
20 contraceptive, which comprises administering to a mammal an effective dose of the sustained-release composition according to claim 3.

25. A method for preventing recurrence of breast cancer after the operation for premenopausal breast cancer, which comprises administering to a mammal an effective dose
25 of the sustained-release composition according to claim 3.

26. A process for producing a lactic acid-glycolic acid polymer having weight average molecular weight of about 8,000 to about 15,000 and having a ratio of weight average molecular weight to number average molecular weight of about 1.90 or lower, or a salt thereof, which comprises adding water to an organic solvent containing a lactic acid-glycolic acid polymer having weight average molecular weight of about 5,000 to 15,000 at a ratio of less than about 5 to 50 (ratio by volume) relative to 100 of the organic solvent.

27. The process for producing a polymer according to claim 26, wherein the organic solvent is hydrophilic.

28. The process for producing a polymer according to claim 27, wherein the hydrophilic organic solvent is acetone.

29. The process for producing a polymer according to claim 26, wherein the ratio of water relative to 100 of the organic solvent is about 10 to about 45 (ratio by volume).

30. The process for producing a polymer according to claim 26, wherein the ratio of water relative to 100 of the organic solvent is about 40 (ratio by volume).

31. A lactic acid-glycolic acid polymer having weight average molecular weight of about 8,000 to about 15,000 and having a ratio of weight average molecular weight to number average molecular weight of about 1.90 or lower, or a salt

thereof.

32. Use of lactic acid-glycolic acid polymer or salt thereof according to claim 31 for producing the sustained-release composition which does not include gelatin.

5 33. A microsphere containing a lactic acid-glycolic acid polymer having weight average molecular weight of about 11,600 to about 14,000 or a salt thereof, and a LH-RH derivative or a salt thereof, and not containing gelatin.

10 34. The microsphere according to claim 33, wherein the LH-RH derivative or a salt thereof is a peptide represented by the formula:

5-oxo-Pro-His-Trp-Ser-Tyr-Y-Leu-Arg-Pro-Z

15 wherein Y denotes DLeu, DAla, DTrp, DSer(tBu), D2Nal or DHis(ImBzl), and Z denotes HH, C₂H₅ or Gly-NH₂, or a salt thereof.

35. The microsphere according to claim 33, wherein the LH-RH derivative or a salt thereof is a peptide represented by the formula:

5-oxo-Pro-His-Trp-Ser-Tyr-DLeu-Leu-Arg-Pro-NH-C₂H₅,

20 or acetate thereof.

36. The microsphere according to claim 33, wherein the LH-RH derivative or a salt thereof is contained at about 5% (w/w) to about 24% (w/w).

25 37. The microsphere according to claim 33, which is a microcapsule.

38. The microsphere according to claim 33, wherein the LH-RH derivative or a salt thereof is released during at least more than 2 weeks.

39. An agent for preventing or treating prostate
5 cancer, prostatomegaly, endometriosis, hysteromyoma, metrofibroma, precocious puberty and dysmenorrhea, or a contraceptive, which comprises the microsphere according to claim 33.

40. An agent for preventing recurrence of breast
10 cancer after the operation for premenopausal breast cancer, which comprises the microsphere according to claim 33.

41. A method for preventing or treating prostate cancer, prostatomegaly, endometriosis, hysteromyoma, metrofibroma, precocious puberty and dysmenorrhea, or a
15 contraceptive, which comprises administering to a mammal an effective dose of the microsphere according to claim 33.

42. A method for preventing recurrence of breast cancer after the operation for premenopausal breast cancer, which comprises administering to a mammal an effective dose
20 of the microsphere according to claim 33.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
9 January 2003 (09.01.2003)

PCT

(10) International Publication Number
WO 03/002091 A3

(51) International Patent Classification⁷: A61K 9/16,
38/09, A61P 5/06, 15/00, A61K 9/50

(21) International Application Number: PCT/JP02/06526

(22) International Filing Date: 28 June 2002 (28.06.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
2001-199462 29 June 2001 (29.06.2001) JP
2001-340980 6 November 2001 (06.11.2001) JP

(71) Applicant (for all designated States except US): **TAKEDA
CHEMICAL INDUSTRIES, LTD.** [JP/JP]; 1-1,
Doshomachi 4-chome, Chuo-ku, Osaka-shi, Osaka
541-0045 (JP).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **YAMAMOTO,
Kazumichi** [JP/JP]; 341-11-1109, Shimizu-cho, Kawara-
machi-dori Nijo-agaru, Nakagyo-ku, Kyoto-shi, Kyoto
604-0911 (JP). **YAMADA, Akiko** [JP/JP]; 313-501,
Sashimono-cho, Kawaramachi-dori Ebisugawa-agaru,
Nakagyo-ku, Kyoto-shi, Kyoto 604-0903 (JP). **HATA,
Yoshio** [JP/JP]; 531-161, Azahonbetsu, Shikabe-cho,
Kayabe-gun, Hokkaido 041-1404 (JP).

(74) Agents: **AOYAMA, Tamotsu** et al.; AOYAMA & PART-
NERS, IMP Building, 3-7, Shiromi 1-chome, Chuo-ku, Os-
aka-shi, Osaka 540-0001 (JP).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KR, KZ, LC, LK,
LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX,
MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI,
SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN,
YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GI, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR,
GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent
(BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR,
NE, SN, TD, TG).

Published:

— with international search report

(88) Date of publication of the international search report:
24 July 2003

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: SUSTAINED-RELEASE COMPOSITION COMPRISING LACTIC ACID-GLYCOLIC ACID COPOLYMER AND
PROCESS FOR PRODUCING THE SAME

(57) Abstract: Present invention is to provide a sustained-release composition which contains a physiologically active substance in high content even when gelatin is not included, and suppresses its initial excessive release and, thus, can achieve a stable release rate over about one month. A sustained-release composition containing a lactic acid-glycolic acid polymer having a ratio or weight average molecular weight and number average molecular weight of about 1.90 or lower, or a salt thereof, and a physiologically active substance.

WO 03/002091 A3

INTERNATIONAL SEARCH REPORT

International Application No

PCT/JP 02/06526

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 A61K9/16 A61K38/09 A61P5/06 A61P15/00 A61K9/50

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 A61K A61P

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, EMBASE, MEDLINE, BIOSIS, FSTA, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 00 35990 A (HATA YOSHIO ;IGARI YASUTAKA (JP); TAKEDA CHEMICAL INDUSTRIES LTD () 22 June 2000 (2000-06-22) the whole document ---	1-42
X	EP 1 048 301 A (TAKEDA CHEMICAL INDUSTRIES LTD) 2 November 2000 (2000-11-02) page 6, line 30,31 ---	1-42
X	EP 0 633 020 A (TAKEDA CHEMICAL INDUSTRIES LTD) 11 January 1995 (1995-01-11) claims; examples --- -/-	1-42

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the International filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

29 November 2002

Date of mailing of the international search report

05/12/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3018

Authorized officer

Skjöldebrand, C

INTERNATIONAL SEARCH REPORT

International Application No

PCT/JP 02/06526

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	KOSTANSKI J W ET AL: "Preparation, characterization, and in vitro evaluation of 1- and 4-month controlled release orntide PLA and PLGA microspheres." PHARMACEUTICAL DEVELOPMENT AND TECHNOLOGY. UNITED STATES 2000, vol. 5, no. 4, 2000, pages 585-596, XP009001300 ISSN: 1083-7450 abstract table 2	1-42
X	OGAWA Y ET AL: "CONTROLLED-RELEASE OF LEUPROLIDE ACETATE FROM POLYLACTIC ACID OR COPOLY-LACTIC-GLYCOLIC ACID MICROCAPSULES INFLUENCE OF MOLECULAR WEIGHT AND COPOLYMER RATIO OF POLYMER" CHEMICAL & PHARMACEUTICAL BULLETIN (TOKYO), vol. 36, no. 4, 1988, pages 1502-1507, XP001120337 ISSN: 0009-2363 abstract page 1503, paragraph 1	1-42
P,X	TAKENAGA M ET AL: "A novel sustained-release formulation of insulin with dramatic reduction in initial rapid release" JOURNAL OF CONTROLLED RELEASE, ELSEVIER SCIENCE PUBLISHERS B.V. AMSTERDAM, NL, vol. 79, no. 1-3, 19 February 2002 (2002-02-19), pages 81-91, XP004340914 ISSN: 0168-3659 abstract; table 2	1-42
X	HIROAKI OKADA ET AL: "BIODEGRADABLE MICROSPHERES IN DRUG DELIVERY" CRITICAL REVIEWS IN THERAPEUTIC DRUG CARRIER SYSTEMS, XX, XX, vol. 12, no. 1, 1995, pages 1-99, XP000604141 ISSN: 0743-4863 page 20-40 page 46-74	1-42

-/--

INTERNATIONAL SEARCH REPORT

International Application No

PCT/JP 02/06526

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	OKADA H: "ONE- AND THREE-MONTH RELEASE INJECTABLE MICROSPHERES OF THE LH-RH SUPERAGONIST LEUPRORELIN ACETATE" ADVANCED DRUG DELIVERY REVIEWS, AMSTERDAM, NL, vol. 28, 1997, pages 43-70, XP001040332 ISSN: 0169-409X abstract page 47, column 1, paragraph 2 figure 4 page 55, column 2, paragraph 4.2 ---	1-42
X	NIWA T ET AL: "PREPARATIONS OF BIODEGRADABLE NANOSPHERES OF WATER-SOLUBLE AND INSOLUBLE DRUGS WITH D,L-LACTIDE/GLYCOLIDE COPOLYMER BY A NOVEL SPONTANEOUS EMULSIFICATION SOLVENT DIFFUSION METHOD, AND THE DRUG RELEASE BEHAVIOR" JOURNAL OF CONTROLLED RELEASE, ELSEVIER SCIENCE PUBLISHERS B.V. AMSTERDAM, NL, vol. 25, no. 1 / 2, 27 May 1993 (1993-05-27), pages 89-98, XP000361370 ISSN: 0168-3659 abstract page 90, column 2, paragraph 2 table 2 ---	1, 4-9, 13-32
X	JEYANTHI R ET AL: "EFFECT OF PROCESSING PARAMETERS ON THE PROPERTIES OF PEPTIDE-CONTAINING PLGA MICROSPHERES" JOURNAL OF MICROENCAPSULATION, TAYLOR AND FRANCIS INC. LONDON, GB, vol. 14, no. 2, 1 March 1997 (1997-03-01), pages 163-174, XP000643342 ISSN: 0265-2048 abstract; table 1 ---	1, 2, 4-9, 13-32
X	MOHR D ET AL: "Gamma irradiation for terminal sterilization of 17beta-estradiol loaded poly-(d,l-lactide-co-glycolide) microparticles" JOURNAL OF CONTROLLED RELEASE, ELSEVIER SCIENCE PUBLISHERS B.V. AMSTERDAM, NL, vol. 61, no. 1-2, 27 August 1999 (1999-08-27), pages 203-217, XP004362977 ISSN: 0168-3659 abstract; table 1 --- -/--	1, 4-9, 13-32

INTERNATIONAL SEARCH REPORT

International Application No

PCT/JP 02/06526

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>SANDERS L M ET AL: "CONTROLLED RELEASE OF A LUTEINIZING HORMONE-RELEASING HORMONE ANALOGUE FROM POLY(D,L-LACTIDE-CO-GLYCOLIDE) MICROSPHERES" JOURNAL OF PHARMACEUTICAL SCIENCES, AMERICAN PHARMACEUTICAL ASSOCIATION. WASHINGTON, US, vol. 73, no. 9, September 1984 (1984-09), pages 1294-1297, XP000942987 ISSN: 0022-3549 the whole document</p>	1-42

INTERNATIONAL SEARCH REPORT

International application No.
PCT/JP 02/06526

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☒ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
Although claims 24, 25, 41, 42 are directed to a method of treatment of the human/animal body, the search has been carried out and based on the alleged effects of the composition.
2. ☒ Claims Nos.: 1-42 (in part)
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
see FURTHER INFORMATION sheet PCT/ISA/210
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this International application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

Continuation of Box I.2

Claims Nos.: 1-42 (in part)

Present claims 1-32 relate to a composition/processes/uses defined (inter alia) by reference to a parameter:

a PLGA polymer "having a ratio of weight average molecular weight to number average molecular weight of about 1.9 or lower"

The use of this parameters in the present context is considered to lead to a lack of clarity within the meaning of Article 6 PCT. It is impossible to compare the parameters the applicant has chosen to employ with what is set out in the prior art, as the polydispersity (Mw/Mn) is not necessarily explicitly mentioned. The lack of clarity is such as to render a meaningful complete search impossible. Consequently, only a fraction of those documents that are possibly novelty-destroying can be cited.

Moreover, In claims 33-42, no reference is made to the polydispersity (Mn/Mw) but only to the Mw-value of the PLGA-polymer. This introduces doubt on what the essential technical feature really is to achieve the slow-release profile. The current set of claims is therefore contradictory (lack of clarity, Art 6 PCT).

The independent claims specify the therapeutic agent as "a physiologically active substance". Said claims are not fully supported by the description (Art. 6 PCT), because the examples all relate to a LH-RH derivative peptide.

Due to the above reasons, the initial phase of the search revealed a very large number of documents relevant to the issue of novelty. So many documents were retrieved that it is impossible to determine which parts of the claims may be said to define subject-matter for which protection might legitimately be sought (Article 6 PCT). For these reasons, a meaningful search over the whole breadth of the claims is impossible. Consequently, the search has been restricted to: sustained release compositions containing PLGA where the active agent is a LH-RH derivative and thier production.

The applicant's attention is drawn to the fact that claims, or parts of claims, relating to inventions in respect of which no international search report has been established need not be the subject of an international preliminary examination (Rule 66.1(e) PCT). The applicant is advised that the EPO policy when acting as an International Preliminary Examining Authority is normally not to carry out a preliminary examination on matter which has not been searched. This is the case irrespective of whether or not the claims are amended following receipt of the search report or during any Chapter II procedure.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/JP 02/06526

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 0035990	A	22-06-2000	AU 1797800 A CN 1334834 T EP 1158014 A1 WO 0035990 A1 JP 2000234016 A	03-07-2000 06-02-2002 28-11-2001 22-06-2000 29-08-2000
EP 1048301	A	02-11-2000	AU 1889799 A BR 9906903 A CA 2316273 A1 EP 1048301 A1 HR 20000471 A1 HU 0100221 A2 NO 20003530 A PL 341733 A1 SK 10272000 A3 CN 1288387 T JP 11269094 A WO 9936099 A1 TR 200002059 T2	02-08-1999 12-12-2000 22-07-1999 02-11-2000 31-12-2000 28-06-2001 14-09-2000 07-05-2001 18-01-2001 21-03-2001 05-10-1999 22-07-1999 22-01-2001
EP 0633020	A	11-01-1995	AT 184480 T AU 674077 B2 AU 6614594 A CA 2127317 A1 CN 1106653 A DE 69420632 D1 DE 69420632 T2 EP 0633020 A1 FI 943205 A JP 8003055 A NO 942515 A NZ 260909 A US 5534269 A	15-10-1999 05-12-1996 12-01-1995 06-01-1995 16-08-1995 21-10-1999 02-03-2000 11-01-1995 06-01-1995 09-01-1996 06-01-1995 27-04-1995 09-07-1996

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☒ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.